

Find the right product for your application



General Purpose

LOCTITE® 401™
LOCTITE® 406™
LOCTITE® 454™

High Gap Fill

LOCTITE® 3090™

General Maintenance

LOCTITE® 407™
LOCTITE® 416™
LOCTITE® 424™
LOCTITE® 4471™

Toughened

LOCTITE® 410™
LOCTITE® 435™
LOCTITE® 438™
LOCTITE® 480™

Low Odour / Low Bloom

LOCTITE® 403™
LOCTITE® 408™
LOCTITE® 460™



General Purpose

INSTANT ADHESIVES



401™
Low Viscosity



Viscosity: 110 mPa.s



Fixture Speed: 5 seconds
Full Cure: 24 hours



Strength: 20 N/mm²

Colour: Clear

Temperature Resistance: 120°C



406™
Wicking Grade



Viscosity: 20 mPa.s



Fixture Speed: 20-45 seconds
Full Cure: 24 hours



Strength: 15.5 N/mm²

Colour: Clear

Temperature Resistance: 120°C



454™
No-Run Gel



Viscosity: Gel



Fixture Speed: 30-60 seconds
Full Cure: 24 hours



Strength: 20.9 N/mm²

Colour: Clear

Temperature Resistance: 120°C

High Gap Fill

INSTANT ADHESIVES



3090™
Two-component Gel



Viscosity: Gel



Fixture Speed: 90-180 seconds
Full Cure: 24 hours



Strength: 21 N/mm²

Colour: Clear to Slightly Cloudy

Temperature Resistance: 80°C

