

# Damaged Rubber Parts



**PC 7350™**  
**Conveyor Belt**  
**Repair**  
 Self-Leveling

**Working Time:** 7 minutes

**Cure Speed:** 2 Hours

**Substrate:** Rubber  
**Form:** Self-Leveling




**PC 7383™ Rubber**  
**Compound**

High Impact, Abrasion-Resistant

**Working Time:** 50 minutes

**Cure Speed:** 24 Hours

**Substrate:** Rubber  
**Form:** Trowelable



## RUBBER REPAIR

Product	Item Number	Package Size	Coverage @6mm thickness	Colour	Tensile Strength (N/mm <sup>2</sup> )	% Elongation	Shore A Hardness	Working Time (min.)	Functional Cure at 25°C
<b>PC 7350™</b>	2073202	400 ml	567 cm <sup>2</sup>	Mixed: Black	11	275	87	7	2 hrs
<b>PC 7383™</b>	2719844	1 kg	1,200 cm <sup>2</sup>	Black	15	26	90	50	24 hrs

## REBUILD EPOXIES

Product	Item Number	Package Size	Coverage @6mm thickness	Colour	Compressive Strength (N/mm <sup>2</sup> )	Tensile Strength (N/mm <sup>2</sup> )	Shore D Hardness	Working Time (min.)	Functional Cure at 25°C
---------	-------------	--------------	-------------------------	--------	---	---------------------------------------	------------------	---------------------	-------------------------

### STICK

<b>EA 3463™</b>	209681	113 g	10 cm <sup>2</sup>	Metallic Black	50	18	70	3	10 mins
-----------------	--------	-------	--------------------	----------------	----	----	----	---	---------

### TROWELABLE

<b>EA 3478™</b>	209822	408 g	323 cm <sup>2</sup>	Dark Grey	125	38	86	20	6 hrs
<b>EA 3471™</b>	219292	454 g	278 cm <sup>2</sup>	Steel Grey	70	27.8	82	30	6 hrs
<b>EA 3473™</b>	219293	454 g	370 cm <sup>2</sup>	Steel Grey	51	27	80	4	10 mins
<b>PC 7222™</b>	209827	1.35 kg	1,020 cm <sup>2</sup>	Grey	72	21	85	30	6 hrs